



# TECHNICAL DATA SHEET

## Light Green

**Product Description:** **Light Green** is designed to create a light green to a rural green patina on bronze, brass, and copper. Supplied as a ready to use formula, Light Green should not be diluted but instead applied directly to the cleaned metal surface. Light Green will also work on bronze, brass, copper, and iron Metal Coatings. When applied on the Iron Metal Coatings, it will create a nice rust finish.

**Safety:** Use in a well ventilated area. Always wear goggles or face shield, vapor respirator, protective clothing and gloves when handling the product.

**Directions:** **1)** Clean the metal with Sculpt Nouveau Metal Cleaner and Degreaser and a Scotch-Brite pad, rinse with water after a few minutes. For more consistent and better reactions, sanding or sandblasting is recommended. Cleaning the surface is mandatory after sanding or handling with bare hands.

**DO NOT** use Acetone or any solvent based cleaners.

**2)** Apply Light Green to the metal surface or Metal Coating surface, by brush, sponge, roll, or spray, however you get the patina on the metal, it will react with the surface but it may show characteristics based on application method. Spraying is the most common method for uniform finishes and sponging is nice for more of a mottled finish. Normal reaction time is multiple hours even though it will start showing some changes within the first hour. It is recommended to apply the patina, then leave it alone overnight. **DO NOT** rinse this patina; it is designed to dry on the surface.

**3)** After 24 hours, if desired, you can reapply the patina, apply a different patina, or burnish the finish back. Try not to apply heavy additional coats, only light additional coats should be added to avoid causing the patina to flake. For burnishing, use water, micro fiber towels, or 0000 steel wool to achieve the look you desire.

**4)** After 24-48 hours after you apply the patina, you can clear coat the metal. Heat the metal with a heat gun or allow it to dry on its own. In any case, you need to be sure that there is no excess moisture retained in the metal surface or this will cause the patina and clear coat to not adhere properly. Apply desired clear coat such as Clear Guard EF or Ever Clear.

**Before Using:** Please read, understand, and follow all the precautions shown on the product label and on the Safety Data Sheets.

The Safety Data Sheets can be found on our website: [www.sculptnouveau.com](http://www.sculptnouveau.com)

### Technical Data

Physical State: Green liquid

Boiling Point: > 100°C (>212°F)

Coverage: About 200 Sq. Ft. Per Gallon

Solubility In Water: Complete  
PH: 2.2

V.O.C.: Not applicable

Metals that it is designed

Flammability Limits: Not flammable

to be used on: Bronze, Brass, and Copper

Phone: +760 432 8242

Fax: 760 741 1074

Sculpt Nouveau, LLC  
1155 Industrial Ave  
Escondido, CA, 92029

E-Mail:  
[info@sculptnouveau.com](mailto:info@sculptnouveau.com)  
Website:  
[www.sculptnouveau.com](http://www.sculptnouveau.com)